

# Industrial Coatings A-20

## Fast Drying Modified Alkyd Coating



Description	Fast Drying Modified Alkyd Coating
Recommended Use	Recommended as an economical topcoat over quality primers. Designed for structural steel surfaces in moderate environments. Not recommended for immersion service.
Mixing Ratio	Single component
Volume Solids	52%
Pot Life	
DFT recommended	1.5 - 2.0 mils
Spreading Rate (Theoretical), ft <sup>2</sup> /gal @ 1 mil	815
Indicated WFT	3.0 - 4.0 mils
Colors	Refer to Comex Color chart
V.O.C. lb/gal	3.63
Dry to touch	6 hours maximum
Fully cured	72 hours
Packaging	1 can contains 1 gallon of product. <i>Weight: 11.42 lb</i> 1 pail contains 5 gallons of product. <i>Weight: 54.78 lb</i>