

Industrial Coatings E-10

High Solids Epoxy Coating



Description	High Solids Epoxy Coating
Recommended Use	Anti-corrosive primer over exterior surfaces as part of a system that includes two component polyurethane topcoats to provide long-lasting protection, color retention and gloss. May be applied over moderately rusted surfaces as long as all loose rust has been removed. Recommended for the protection of steel, concrete, and masonry surfaces, concrete floors, brickwork, exterior tanks, pipes, and other surfaces exposed to chemical or marine weathering.
Mixing Ratio	1:1
Volume Solids	70%
Pot Life	2 hours at 70°F 1 hour at 90°F
DFT recommended	4.0 - 6.0 mils
Spreading Rate (Theoretical), ft ² /gal @ 1 mil	1123
Indicated WFT	6.0 - 8.5 mils
Colors	Refer to Comex Color chart
V.O.C. lb/gal	2.17
Dry to touch	36 hours max.
Fully cured	30 days
Packaging	1-gallon pack <i>Weight: 12.66 lb</i> 1 can contains 0.5 gallon of resin <i>Weight: 6.66 lb</i> 1 can contains 0.5 gallon of cure <i>Weight: 6.00 lb</i> 5-gallons pack <i>Weight: 60.52 lb</i>