

Industrial Coatings U-10

High Solids, Gloss Polyurethane Topcoat



Description	High Solids, Gloss Polyurethane Topcoat
Recommended Use	Protection for exterior industrial and architectural structural steel. Excellent coating for steel tanks and pipelines subject to severe weathering environments and concrete walls and floors subject to abrasion. Can be applied as OEM for industrial equipment such as hoppers and transportation vehicles. Not recommended for immersion service.
Mixing Ratio	4:1
Volume Solids	70%
Pot Life	2 hours at 70°F 1 hour at 90°F
DFT recommended	3.0 - 5.0 mils
Spreading Rate (Theoretical), ft ² /gal @ 1 mil	1123
Indicated WFT	5.0 - 7.0 mils
Colors	Refer to Comex color chart
V.O.C. lb/gal	2.59
Dry to touch	24 hours max.
Fully cured	30 days
Packaging	1-gallon pack <i>Weight: 11.73 lb (5.32 Kg)</i> 1 can contains 0.8 gallon (3.03 L) of resin <i>Weight: 9.61 lb (4.36 Kg)</i> 1 can contains 0.2 gallon (0.76 L) of cure <i>Weight: 2.12 lb (0.96 Kg)</i> 5-gallons pack <i>Weight: 55.90 lb (25.41 kg)</i> 1 pail contains 4 gallons (15.14 L) of resin <i>Weight: 45.70 lb (20.73 Kg)</i> 1 can contains 1 gallon (3.78 L) of cure <i>Weight: 10.33 (4.68 Kg)</i>