

# Industrial Coatings U-50

## High Gloss Polyurethane Topcoat



Description	High Gloss Polyurethane Topcoat
Recommended Use	Recommended for industrial and moderate marine environments. Outstanding performance on concrete floors subjected to harsh abrasion. Good resistance to continued detergent cleaning. Resistant to occasional spills and splatters of mild chemicals. This product is not recommended for immersion service.
	4:1
Mixing Ratio	50%
Volume Solids	4 hours at 70°F
Pot Life	1 hour at 90°F
	2.5 - 3.0 mils
DFT recommended	802
Spreading Rate (Theoretical), ft <sup>2</sup> /gal @ 1 mil	5.0 - 6.0 mils
Indicated WFT	Refer to Comex color chart
Colors	3.75
V.O.C. lb/gal	24 hours max.
Dry to touch	30 days
Fully cured	1-gallon pack <i>Weight 11.53 lb (5.23 Kg)</i>
Packaging	1 can contains 0.8 gallon (3.03 L) of resin <i>Weight: 9.41 lb (4.27 Kg)</i>
	¼ gallon can contain 0.2 gallon (0.76 L) of cure <i>Weight: 2.12 lb (0.96 Kg)</i>
	5-gallons pack <i>Weight 54.99 lb (24.95 Kg)</i>
	1 can contains 4 gallons (15.14 L) of resin <i>Weight: 44.68 lb (20.27 Kg)</i>
	1 can contains 1 gallon (3.78 L) of cure <i>Weight: 10.33 (4.68 Kg)</i>