

Industrial Coatings ZR-10

Zinc Rich Epoxy Primer



Description	Zinc Rich Epoxy Primer
Recommended Use	Recommended as a primer for new steel work as well as for maintenance of properly prepared steel structures, tanks and pipelines. May be used as a primer for high performance epoxy, urethane systems.
Mixing Ratio	3.25 parts of Resin (Component A) 1.00 part of Cure (Component B) 0.75 parts or Powder (Component C)
Volume Solids	70%
Pot Life	16 hours at 70°F 2 hour at 90°F
DFT recommended	3.0 mils
Spreading Rate (Theoretical), ft ² /gal @ 1 mil	1123
Indicated WFT	4.0 - 5.0 mils
Colors	Gray
V.O.C. lb/gal	2.08
Dry to touch	36 hours max.
Fully cured	1-gallon pack <i>Weight: 23.13 lb (10.49 Kg)</i>
Packaging	1 can contains 0.65 gallon (2.45 L) of resin <i>Weight: 11.66 lb (5.29 Kg)</i> 1 can contains 0.15 gallon (0.575 L) of powder <i>Weight: 9.08 lb (4.12 Kg)</i> 1 can contain 0.20 gallon (0.76 L) of cure <i>Weight: 2.17 lb (0.98 Kg)</i>