

## 1900 PRO FINISH INTERIOR SATIN LATEX FINISH



A commercial quality latex wall and trim paint for interior surfaces. Suitable for residential and commercial painting where a higher level of performance is desired compared to builder or maintenance paints. Pro Finish 1900 has excellent scrub resistance and high film build.

### Benefits:

- Rich, satin finish for walls and trim.
- Excellent wash ability and superior performance over standard flat wall finishes.
- Fast drying, low odor and soap and water clean up.
- Its use on new or repaint surfaces assures superior, uniform finish results.

### Surface Preparation and Primer Recommendations

#### INTERIOR

Surface	Preparation	Primer
Wood	KPS1, KPS2	KSU1
Drywall	KPS6	KSU3
Concrete / Masonry	KPS4	KSU2
CMU	KPS5	KSU2
Ferrous Metal	KPS7	KSU4
Non-Ferrous Metal	KPS8	KSU4

#### EXTERIOR

Not intended for exterior application.

### Where to Use:

- Recommended for properly prepared interior drywall, plaster, concrete, wood, previously painted or primed metal.

Limitations: Not intended for high humidity areas.

Colors: White and light to medium custom Color Life colors.

Type/Thinner: Latex/water. This product is packaged ready to use.

Type: Vinyl Acrylic Emulsion

Finish: Satin

Sheen: 15% to 22% @ 60°

Solids by Volume: 37.02%

### How to Apply:

- Stir well with lifting motion
- Apply by brush, roller or airless spray

Surface Temp: Temperature should be above 50°F and below 95°F. Avoid frost, fog and damp conditions.

Coverage: 400 ft<sup>2</sup> @ 1.5 MIL dry film

\*Coverage will vary depending on application method, surface texture, porosity and color.

Drying Time: Dries to the touch in 1 hour, may be re-coated after 4 hours. Drying time will vary depending on temperature, air circulation and humidity.

VOC: Maximum of 100 g/l

Clean-Up: Clean all application equipment with soap and warm water.

\*All surfaces must be sound, dry, clean and free from dirt, oil, wax grease, mildew, loose or peeling paint and other foreign material.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith and limited guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them. Specifications subject to change without notice.

July 16, 2008