

## 1903 ACCU-TONE EGGSHELL LATEX ENAMEL

A commercial quality latex wall and trim paint for interior surfaces. Suitable for residential and commercial painting where a higher level of performance is desired compared to builder or maintenance paints. An extremely durable paint that dries to a washable finish.

### Benefits:

- Non-yellowing, washable and stain resistant.
- Ideally suited for commercial and residential use.
- Excellent working properties, hiding characteristics and low odor.
- Easy to apply with soap and water clean up.

### Surface Preparation and Primer Recommendations

#### INTERIOR

Surface	Preparation	Primer
Wood	KPS1, KPS2	KSU1
Drywall	KPS6	KSU3
Concrete / Masonry	KPS4	KSU2
CMU	KPS5	KSU2
Ferrous Metal	KPS7	KSU4
Non-Ferrous Metal	KPS8	KSU4

#### EXTERIOR

Not intended for exterior application.

\*All surfaces must be sound, dry, clean and free from dirt, oil, wax grease, mildew, loose or peeling paint and other foreign material.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith and limited guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them. Specifications subject to change without notice.

July 16, 2008



### MPI 44

#### Where to Use:

- Recommended for properly prepared new or repaint work on interior plaster, gypsum board, masonry, concrete, wood, and metal.

Limitations: Not intended for use over lime containing plaster, floors or decks.

Colors: White and light to dark custom Color Life colors.

Type/Thinner: Latex/water. This product is packaged ready to use.

Type: Vinyl Acrylic Emulsion

Finish: Eggshell

Sheen: 6% to 8% @ 60°

Solids by Volume: 33.11%

#### How to Apply:

- Stir well with lifting motion
- Apply by brush, roller or airless spray

Surface Temp: Temperature should be above 50°F and below 95°F. Avoid frost, fog and damp conditions.

Coverage: 360 ft<sup>2</sup> @ 1.5 MIL dry film

\*Coverage will vary depending on application method, surface texture, porosity and color.

Drying Time: Dries to the touch in 1 hour, may be re-coated after 4 hours. Drying time will vary depending on temperature, air circulation and humidity.

VOC: Maximum of 110 g/l

Clean-Up: Clean all application equipment with soap and warm water.