



5510 SERIES TILT-TEX X ELASTO 100% ACRYLIC TEXTURE COATING

A high quality, durable, exterior elastomeric / acrylic finish for a wide variety of cementitious surfaces. This product offers increased resistance to soluble salts (efflorescence) water and wear. Tilt-TEX X offers excellent adhesion, color retention, durability, and resistance to weathering and moisture.

Benefits:

- Outstanding adhesion to primed concrete and masonry.
- Ideally suited for commercial and residential use.
- Excellent bridging qualities over hairline cracks.
- Easy to apply with soap and water clean up.

Available texture grades:

- 5510 Tilt-TEX X Fine Texture
- 5511 Tilt-TEX X Medium Texture
- 5512 Tilt-TEX X Coarse Texture

Surface Preparation and Primer Recommendations

INTERIOR

Interior application specifications available. Contact your Field sales representative for recommendations.

EXTERIOR

Surface	Preparation	Primer
Wood	KPS9	KSU1
Drywall	KPS14	KSU7
Concrete / Masonry	KPS12	KSU5
CMU	KPS13	KSU5
Hardboard Siding	KPS10	KSU6
Cementitious Siding	KPS11	KSU6
Ferrous Metal	KPS15	KSU4
Non-Ferrous Metal	KPS16	KSU4

*All surfaces must be sound, dry, clean and free from dirt, oil, wax grease, mildew, loose or peeling paint and other foreign material.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith and limited guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them. Specifications subject to change without notice.

July 16, 2008

Where to Use:

- Recommended for properly prepared new or repaint work on exterior masonry, concrete and wood.

Limitations: Not intended for use on horizontal surfaces, floors or decks.

Colors: White and light to medium custom Color Life colors.

Type/Thinner: Latex/water. This product is packaged ready to use.

Type: Elastomeric / 100% Acrylic Emulsion

Finish: Flat

Sheen: Less than 5% @ 60°

Solids by Volume: 62.56%

How to Apply:

- Stir well with lifting motion
- Apply by airless spray.
- Application by brush and roller limits appearance of finished texture.

Surface Temp: Temperature should be above 50°F and below 95°F. Avoid frost, fog and damp conditions.

Coverage: 670 ft² @ 1.5 MIL dry film (Theoretical coverage expected will be between 45 and 125 ft² on intended applications.) *Coverage will vary depending on application method, surface texture, porosity and color.

Drying Time: Dries to the touch in 2 hours, may be re-coated after 8 hours. Drying time will vary depending on temperature, air circulation and humidity.

VOC: Maximum of 50 g/l

Clean-Up: Clean all application equipment with soap and warm water.

ASTM Applicable Standards

ASTM E84 Class A Rating-----	Passes
ASTM E96 Water Vapor Transmission-----	5 to 8 Perms
ASTM B117 Salt Spray Apparatus-----	Passes
ASTM G153 Accelerated Outdoor Exposure-----	Passes
ASTM D522 Mandrel Bend Test 1"-----	Passes
ASTM D2243 Freeze Thaw 50 Cycles-----	Passes
ASTM D2370 Elongation-----	250% @ 70° F 110% @ 0° F

Federal Standards

TT-C-555B----- Meets performance standards.