

8110 EMBASSY WB 100% ACRYLIC GLOSS BLOCK RESISTANT ENAMEL



Our finest acrylic gloss enamel that provides an appearance that is normally associated with alkyd enamels. The excellent flow and high gloss allow it to be used in place of alkyd enamels where a low V.O.C. product is preferred. Our 100% acrylic 8110 Embassy WB is formulated to provide superior gloss and color retention for all interior applications. The look and feel of oil based enamels with the ease of application and clean up of water borne paints.

Benefits:

- Non-yellowing, washable and stain resistant.
- Ideally suited for commercial and residential use.
- Excellent sheen and color retention.
- Easy to apply with soap and water clean up.
- Exceptional maintenance capability.

Surface Preparation and Primer Recommendations

INTERIOR

Surface	Preparation	Primer
Wood	KPS1, KPS2	KSU1
Drywall	KPS6	KSU3
Concrete / Masonry	KPS4	KSU2
CMU	KPS5	KSU2
Ferrous Metal	KPS7	KSU4
Non-Ferrous Metal	KPS8	KSU4

EXTERIOR

Not intended for exterior application.

Where to Use:

- Recommended for properly prepared new or repaint work on interior plaster, gypsum board, masonry, concrete, wood, and metal. Can be applied directly to properly prepared, non-ferrous metals or primed ferrous metals.

Limitations: Not intended for use over lime containing plaster without proper sealing, floors or decks.

Colors: White and light to medium custom Color Life colors.

Type/Thinner: Latex/water. This product is packaged ready to use.

Type: Acrylic Resin

Finish: High Gloss

Sheen: 80% + @ 60°

Solids by Volume: 37.59%

How to Apply:

- Stir well with lifting motion
- Apply by brush, roller or airless spray

Surface Temp: Temperature should be above 50°F and below 95°F. Avoid frost, fog and damp conditions.

Coverage: 400 ft² @ 1.5 MIL dry film

*Coverage will vary depending on application method, surface texture, porosity and color.

Drying Time: Dries to the touch in 1 hour, may be re-coated after 4 hours. Drying time will vary depending on temperature, air circulation and humidity.

VOC: Maximum of 90 g/l

Clean-Up: Clean all application equipment with soap and warm water.

*All surfaces must be sound, dry, clean and free from dirt, oil, wax grease, mildew, loose or peeling paint and other foreign material.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith and limited guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them. Specifications subject to change without notice.

July 16, 2008