

962JB PRO KRAFT 100% ACRYLIC EXTERIOR SATIN FINISH



Our premium exterior satin finish provides fast dry, outstanding adhesion, resistance to weathering and moisture in an easy to apply product. It produces a breathing type finish with extra resistance to blistering and the satin sheen provides low dirt accumulation. Low temperature application (above 38 °F).

Benefits:

- Outstanding satin finish for siding or trim.
- Excellent durability and superior performance over standard finishes.
- Fast drying, low odor and soap and water clean up.
- Its use on new or repaint surfaces assures superior, uniform finish results.

Surface Preparation and Primer Recommendations

INTERIOR

Not intended for interior application.

EXTERIOR

Surface	Preparation	Primer
Wood	KPS9	KSU1
Drywall	KPS14	KSU7
Concrete / Masonry	KPS12	KSU5
CMU	KPS13	KSU5
Hardboard Siding	KPS10	KSU6
Cementitious Siding	KPS11	KSU6
Ferrous Metal	KPS15	KSU4
Non-Ferrous Metal	KPS16	KSU4

*All surfaces must be sound, dry, clean and free from dirt, oil, wax grease, mildew, loose or peeling paint and other foreign material.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith and limited guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them. Specifications subject to change without notice.

July 16, 2008

Where to Use:

- Recommended for properly prepared exterior drywall, plaster, concrete, wood, previously painted or primed metal applications.

Limitations: Not intended for floors or walkways.

Colors: White and light to dark custom Color Life colors.

Type/Thinner: Latex/water. This product is packaged ready to use.

Type: 100% Acrylic Resin

Finish: Satin

Sheen: 15% to 35% @ 60°

Solids by Volume: 32.83%

How to Apply:

- Stir well with lifting motion
- Apply by brush, roller or airless spray

Surface Temp: Temperature should be above 50°F and below 95°F. Avoid frost, fog and damp conditions.

Coverage: 350 ft² @ 1.5 MIL dry film

*Coverage will vary depending on application method, surface texture, porosity and color.

Drying Time: Dries to the touch in 1 hour, may be re-coated after 4 hours. Drying time will vary depending on temperature, air circulation and humidity. Low temperature application is limited to white and medium colors. The surface and air temperature should remain above 38°F. If painting in cold conditions the temperature must not fall below freezing for at least 8 hours after application. Recoat time at lower temperatures require a minimum of 24 hours when temperatures are below 50°F. Do not apply if snow, rain, frost, fog or damp conditions are expected within 24 hours after application.

VOC: Maximum of 120 g/l

Clean-Up: Clean all application equipment with soap and warm water.