



## KPS5 SURFACE PREPARATION INTERIOR GUIDELINES

### CMU (Concrete Masonry Unit, Cinder Block) - NEW

#### To Be Painted

- ⊕ If mildew is present or suspected treat with a 3:1 water and household bleach solution, leaving it on for 20 minutes and adding more as it dries. Wear eye and skin protection. Rinse thoroughly and let dry.
- ⊕ New concrete and masonry, depending on temperature and humidity, requires a minimum of 30 days to dry to insure surface alkalinity is acceptable. The PH should be between 6 and 9 prior to paint application.
- ⊕ Remove any dirt by scrubbing with detergent and water. Rinse thoroughly and let dry.
- ⊕ Dull any glossy areas with medium (120) grit sandpaper. Wear eye protection, dust mask and work gloves.
- ⊕ Remove any loose or protruding mortar excess by a stiff scraper or wire brush.
- ⊕ Fill any gouges with concrete patch; let dry and sand flush.
- ⊕ Fill gaps (1/8" to 1/4") with quality acrylic or siliconized acrylic caulk, and immediately smooth it flush. Allow to dry over night and make a second application if needed. Do not sand caulk applications.
- ⊕ Gaps larger than 1/4" should be prefilled with foam backer rod prior to application of a quality acrylic or siliconized acrylic caulk.

### CMU (Concrete Masonry Unit, Cinder Block) - PREVIOUSLY PAINTED

#### To Be Painted

(\*NOTE: If lead is suspected in the original paint, do not attempt to remove paint or scrape, sand, use heat gun, etc., which might release lead into the environment, rather contact a contractor qualified for lead paint assessment and abatement.)

- ⊕ If mildew is present or suspected treat with a 3:1 water and household bleach solution, leaving it on for 20 minutes and adding more as it dries. Wear eye and skin protection. Rinse thoroughly and let dry.
- ⊕ Remove any dirt by scrubbing with detergent and water. Rinse thoroughly and let dry.
- ⊕ Dull any glossy areas with medium (120) grit sandpaper. Wear eye protection, dust mask and work gloves.
- ⊕ Fill gaps (1/8" to 1/4") with quality acrylic or siliconized acrylic caulk, and immediately smooth it flush. Allow to dry over night and make a second application if needed. Do not sand caulk applications.
- ⊕ Gaps larger than 1/4" should be prefilled with foam backer rod prior to application of a quality acrylic or siliconized acrylic caulk.

These suggestions and data are based on information we believe to be reliable. They are offered in good faith and limited guarantee, as conditions and methods of use of our products are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them. Specifications subject to change without notice.